

## ARAMİD FİBER KUMAŞ 170 GR/M2 TWİLL

### Teknik Bilgi:

CHARACTERISTICS		Nominal	Tolerance	Normative
Mass per unit area	gr/sqm.	170	± 5%	ISO 4605
Weave		Twill 2x2		ISO 2113
Standard Width	mm.	1000/1200	± 2,5%	
Laminate thickness	mm.	0,25	± 15%	ISO 5084
Other informations		Loomstate		

Nominal Construction		WARP		WEFT	
Fibre description		HM Aramid Twaron 2200 1210 dtex		HM Aramid Twaron 2200 1210 dtex	
Thread Count	ends/cm.	6,7	ISO 4602	6,7	ISO 4602
Weight distribution	gr/sqm.	HM Aramid	85	HM Aramid	85
	%		50%		50%