

PROTUBE-CS CARBON FIBER SQUARE TUBE TECHNICAL DATA SHEET

Teknik Bilgi:

Product	Carbon Fiber Square Tube	Pulwinding
Construction	Pullwinding	0°, +37°, -37°
Fiber type	Carbon Fiber Roving	TENAX STS40
Resin type	EPOXY	
Fiber Content by Weight	>76	%
Fiber Content by Volume	>65	%
Tensile Strength (Fiber Direction)	>2080	Mpa
Compression Strength (Fiber Direction)	>1450	Mpa
Tensile Modulus (Fiber Direction)	>145	Gpa
Density	>1,51	g/cm ³