

QZ 13, 5101, 5110, 5111 Mould Release Agents

Mould release/sealer QZ 5101	Film forming Poly-Vinyl-Alcohol (P.V.A.) release agent, which can also be used as a sealer for porous surfaces. Produces glossy mouldings.
Mould release QV 5110	Cloth applied wax based release agent for general applications. Polishable to lustre.
Mould release QZ 5111	A liquid suspension of waxes in solvent for the release of general and intricate mould surfaces. Polishable to lustre.
Mould release QZ 13	An easily applied liquid silicone based, solvent and release agent. For use at ambient and elevated temperatures. Blurs fine surface detail and requires complete removal if mouldings are to be painted.

Typical product data and processing

Mould release QZ 5101

Property	Unit	Value
S.G. at 25°C	g/cm ³	0.9
Flash point (DIN 51755)	°C	17
Supplied form	-	Blue liquid
Storage months	5 - 25°C	12

Mould release/sealer QZ 5101 is applied by brush or spray gun in one or more layers. The application of a non-silicone wax may be required for QZ 5101 to coat evenly. without cissing.

Typical product data and processing

Mould release QV 5110

Property	Unit	Value
S.G. at 25°C	g/cm ³	0.8
Flash point (DIN 51755)	°C	>24
Supplied form	-	White paste
Storage months	5 - 25°C	12

Release agent QV 5110 is applied by brush or cloth to the mould surfaces, allowed to dry for 30 min, then polished with a soft cloth.

Typical product data and processing

Mould release QZ 5111

Property	Unit	Value
S.G. at 25°C	g/cm ³	0.7
Flash point (DIN 51755)	°C	<21
Supplied form	-	White liquid
Storage months	5 - 25°C	12

Two or three layers of QZ 5111 are applied by brush or spray gun. Subsequent evaporation of the solvent, approximately 15 mins, results in a hard, polished layer.

QZ 5111 should always be shaken or stirred before use.

Typical product data And processing

Mould release QZ 13

Property	Unit	Value
S.G. at 25°C	g/cm ³	0.86
Flash point (DIN 51755)	°C	15
Supplied form	-	Colourless liquid
Storage months	5 - 25°C	12

Apply QZ 13 by brush or spray in 2 - 3 light applications. QZ 13 contains a flammable solvent. Safety precautions should be taken during use and storage.

Pack Quantities

QV5110	1 kg
QZ13	0.5 kg
QZ5101	0.9 kg
QZ5111	0.75 kg

Related Products

Gloves: - Disposable gloves available in Blue Nitrile, Vinyl & Latex.

Mixing Pots: - Available in 0.5 Litre, 1.0L, 2.5L & 5L

Brushes: - A Range of brushes available for material application

Handling precautions

Caution

Huntsman advanced products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in Vantico publication No. 24264/3/e Hygienic precautions for handling plastics products of Huntsman and in the Material Safety Data sheets for the individual products. These publications are available on request and should be referred to for fuller information.

Huntsman Advanced Materials (UK) Limited

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

© 2004 Huntsman Advanced Materials (Switzerland) GmbH

® Ren, RenShape and parts in Minutes are registered trademarks of Vantico, GnbH, Bsael, Switzerland.

™ Ren Pim is a trademark of Vantico GmbH, Basil, Switzerland